



47-49 2K Matting Agent

APPLICATION DATA



Mixing Ratio : See Series 2000.




Application viscosity : Airspray (sec) : -
DINCUP 4mm/20°C(70°F) Pressure tank (sec) : -
Airless (sec) : -



	<u>Nozzle diameter (mm)</u>	<u>Spraying pressure (bar/psi)</u>
Gravity feed	-	-
Suction feed	-	-
Pressure tank	-	-
Airless	-	-
HVLP	-	See Info Manufacturer
HE	-	See Info Manufacturer



Spray coats / Layer thickness : - / -



Flash-off (min) 20°C/70°F : -



Drying time (min) 20°C/70°F : -
60°C/140°F : -
Obj.



Potlife (min) 20°C/70°F : -

Only for USA; If used as instructed, this product is designed to comply with the US National Volatile Organic Compound (VOC) Emission Standard for Automobile Refinish Coatings. Confirm compliance with state and local air quality rules before use.

The technical data in these publications are based on our present knowledge and give you an idea of the various applications without obligations.

47-49 2K Matting Agent



PRODUCT INFO

- Area of application** : This product is specially developed for the adaptation of the degree of gloss of 2-pack finishes. The amount of matting agent to be added can be found in the paragraph "Gloss". After that, the mixture has to be mixed further with hardener, as described in the documentation of Serie 2000.
- Chemical base** : High-quality hydroxy acrylic resin with silicates.
- General qualities** : Matting Agent. Finish: Depends on added quantity and colour. Add Paste=Degree of gloss (60/60), 20%=50-70% (eggshell gloss), 30%=40-50% (satin gloss), 40%=0-10% (matt). Hint: If you want to use a matted clear coat, you can use 2K Clear Coat Matt.
- Auxiliary materials** : Series 2000

Physical properties	Specific gravity (kg/l)	: 1.038
	Flash point	: Closed cup: 26°C (78.8°F)
	Vol.% solids	: 34
	Economy	: 9 m ² /L/50 µm (2.0 mil)
	Gloss	:
	Color	: Transparent

Substrates : See info Series 2000

Undercoats : See info Series 2000

Finishing materials : See info Series 2000

Cleaning the equipment : 1-051 Gun Cleaner

Storage life (years) : min. 1
(Under normal storage conditions and unopened tins).

Only for USA; If used as instructed, this product is designed to comply with the US National Volatile Organic Compound (VOC) Emission Standard for Automobile Refinish Coatings. Confirm compliance with state and local air quality rules before use.

The technical data in these publications are based on our present knowledge and give you an idea of the various applications without obligations.