



GENERAL INFORMATION

ASE200 is an aerosol self etching primer designed to promote adhesion and improve corrosion resistance over a variety of metal substrates. Recommended for sand throughs and small areas.



1. COMPONENTS

- ASE200 Universal Aerosol Self Etching Primer



2. MIXING RATIO

- Ready to use



3. POT LIFE @ 77°F (25°C)

- Indefinite



4. CLEAN UP

- To clean nozzle: Invert can and spray for about three (3) seconds



5. ADDITIVES

- N/A



6. SURFACE PREPARATION

- Remove all dirt, grease, wax and rust
- Clean with 170 Aqua Clean
- Sand and featheredge all areas to be primed with P320 grit sandpaper
- Reclean surface with 155 Surface Cleaner or 170 Aqua Clean and wipe dry with clean cloth before product flashes

7. TOPCOATS

- N/A



8. TECH NOTES

- N/A



9. SUBSTRATES

- Steel
- Aluminum
- Most types of galvanized steel



10. APPLICATION

- Shake can for two (2) minutes and repeat for 10 seconds after each minute of use
 - Apply two (2) to three (3) thin coats. Dry mils 0.2-0.4 mils/8-10µm
- NOTE:** Surface temperature should be 60-90°F (16-32°C)



11. FLASH / DRY TIMES

- To topcoat: 20 minutes
- May be lightly sanded after 30 minutes



12. INFRARED CURE

- N/A



13. GUN-SET UP

- N/A



14. PHYSICAL DATA

RTS REGULATORY DATA:	AS IS	
	LBS./GAL	g/L
Actual VOC	Not Regulated	Not Regulated
Regulatory VOC (less water and exempt solvents)	Not Regulated	Not Regulated
Density	5.5 - 6.5	660 - 780
	WT.%	VOL.%
Total Volatile Content	85 - 100	95 - 100
Water Content	0	0
Exempt Compound Content	40 - 50	40 - 50
Coating Category	Aerosol Coating (Auto Body Primer)	

NOTES

If used as instructed, this product is designed to comply with the US National Volatile Organic Compound (VOC) Emission Standard for Automobile Refinish Coatings. Confirm compliance with state and local air quality rules before use. The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Valspar assumes no obligation or liability for use of this information. **UNLESS VALSPAR AGREES OTHERWISE IN WRITING, VALSPAR MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. VALSPAR WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.